

# DIBAFIX

## Technical data sheet

---

<u>Material</u>	:	One component material on butyl base
<u>Colour</u>	:	Black
<u>Density</u>	:	1.1 KG/dm <sup>3</sup>
<u>Hardness</u> (Shore 00)	:	60-70
<u>Elongation</u>	:	350 %
<u>Elongation force</u>	:	4.0 N/cm <sup>2</sup>
<u>Tack</u>	:	Peeling strength : 26 N/25 mm Shear strength : 4 N/25 mm
<u>Sag LS 1600 / 8 hrs + 50 °C</u>	:	1 mm
<u>Application Temperature</u>	:	+ 5 °C to + 40 °C
<u>Temperature resistance in operation</u>	:	- 40 °C to + 90 °C
<u>Compatibility</u>	:	
a) Compatible with	:	polycarbonate sheets (eg. Makrlon, Lexan) polyacryl (eg. Plexiglas), polyester roofing material (ECB, EPDM, PIB, CR, PVC, etc.), polystyrene
b) Not compatible with	:	fuels and lubricants on hydrocarbon base, Solvents, starch, acids, etc....
<u>Presentation</u>	:	on rolls

